



ROLCOATING

- Cold coating
- Two-component

Coloured two-component acrylic cold plastic (PMMA).

Environment



Urban space

ADVANTAGES

- Easy to apply with squeegee and foam roller
- Very good adhesion to the road-surface, and also on concrete
- Especially designed for coloured bus lanes, bicycle-tracks, footpath's etc

PERFORMANCES, CERTIFICATIONS AND CONSUMPTIONS

Product rate

Approx. 1,5- 2,0 kg/m² for a thickness of 0,8 – 1,2 mm

Application technique



Manuelle

CONDITIONS FOR USE

■ Application

Manual: mark out the surface, which has to be done, with self-adhesive tape. Mix the Rolcoating and the hardener. Apply with a spatula and level the surface using a roller. Remove adhesive strips after application.

Machine: Rolcoating can be sprayed with a special airless or pneumatic application machine, equipped with 2 circuits and internal (static mixer) or external (double spray) mixing. Benox L40LV liquid is used as hardener.

• Support

Clean and dry floor, new or old hydrocarbon coatings.

• Primer

On dusty and absorbing surfaces or fresh bituminous surfaces, we advise to apply EP primer first.

• Ground temperature limits

Minimum application temperature is 10°C.

• Maximum hydrometry

80 %

• Cleaning

With VG44 or VG40.

• Thinning

If necessary add max. 1% de diluant VG55
Do not use other thinners.

■ Storage

Protected from sunlight and frost, the paint will keep for 6 months in its original packaging. The reference is the manufacturing date affixed to the packaging.



ROLCOATING

PACKING

Rolcoating
16 kg cans

Noviper BP-30 (powder)
115 gram plastic bags

Avox L40S (liquid)
100 gram plastic bags

Benox L40LV
20 kg drums

TECHNICAL CHARACTERISTICS

Colours	Oxide red (\pm RAL3011), Signal red (\pm RAL3001) and Traffic green (\pm RAL6024) are standard-colours. Other colours are available on request.
Skid resistance	SRT > 0,55
Viscosity	Thick fluid compound
Specific Gravity	Approx. 1.8 gram/cm ³
Flashpoint	< 10°C
Mixing ratio	2 bags of 115 grams of Noviper BP-30 or 2 bags of 100 grams of Avox L40S for 16kg of Rolcoating Add 2% Benox L40LV by volume
Potlife	10 minutes by 20°C
Curing time	Approx. 20 minutes by 30°C Approx. 30 minutes by 20°C Approx. 40 minutes by 10°C
Composition	base of colored acrylic resins (PMMA) and sand
Application	Manual or with a suitable machine

SAFETY- ENVIRONMENT

Flammable product for professional use.

Soiled packaging, cleaning and rinsing products are waste to be treated according to current regulations.

Contact our sales department to consult the Safety Data Sheet.

VELUVINE B.V.

Ramshoorn 11
4824 AG Breda, Holland
Tel: 31 76 5421200 • Fax: +31 76 5420288
E-mail : info@veluvine.nl
www.veluvine.nl



AVAILABLE VERSION



NETHERLANDS



UK



FRANCE



SPAIN



GERMANY